



## Tower Orange 5L Tin

Water based Acrylic Emulsion - Tower Orange

### Technical Data

Use	Mild Industrial Environments
Colour	5258 Orange
Solids By Volume	34% - 38%
Dry to touch	1 - 2 hour
Handling Dry	2 - 3 hour
Dry Film Thickness	1.5 - 2.5 mils
Wet Film Requirement	4.0 - 7.0 mils
Coverage (25 Micron DFT)	13.5 - 15.0 sq. m/L
Shelf Time	12 months
Storage Requirement	Protect from Freezing
Thinner	Water
Clean up	Soap and Water

### Adjustment for Tap Water Use

Brush / Roller Application	No Adjustment
Air Spray Application	Add 3-10% Water to adjust to 25-30 seconds in the DIN 4 cup
Application Temperature	+10 C Minimum
Substrate Temperature	+3 C Above dew point
Relative Humidity	85% Maximum

### Safety

Certified None dangerous goods